

IN THE UNITED STATES PATENT AND TRADEMARK OFFICE

In re application of

Guy ROCHE et al.

Serial No. 09/736,365

Filed December 15, 2000



Docket No. 2000_1650A

ENAMEL COMPOSITION FOR DIELECTRIC LAYERS,
WHITE PIGMENTS WITH IMPROVED WETTABILITY
CONTAINED THEREIN AND PLASMA DISPLAY PANEL
CONTAINING THE DIELECTRIC LAYER

CLAIM OF PRIORITY UNDER 35 USC 119

Assistant Commissioner for Patents
Washington, DC 20231

Sir:

Applicants in the above-entitled application hereby claim the date of priority under the International Convention of European Patent Application No. 99 403 161.5, filed December 16, 1999, as acknowledged in the Declaration of this application.

A certified copy of said European Patent Application is submitted herewith.

Respectfully submitted,

Guy ROCHE et al.

By Warren M. Cheek, Jr.
Warren M. Cheek, Jr.
Registration No. 33,367
Attorney for Applicants

WMC/dlk
Washington, D.C. 20006
Telephone (202) 721-8200
January 31, 2001

#27
#5 PD
08/27
5/10/01

THIS PAGE BLANK (USPTO)



Europäisches
Patentamt

Eur pean
Patent Office

Office européen
des brevets



Bescheinigung

Certificate

Attestation

Die angehefteten Unterla-
gen stimmen mit der
ursprünglich eingereichten
Fassung der auf dem näch-
sten Blatt bezeichneten
europäischen Patentanmel-
dung überein.

The attached documents
are exact copies of the
European patent application
described on the following
page, as originally filed.

Les documents fixés à
cette attestation sont
conformes à la version
initialement déposée de
la demande de brevet
européen spécifiée à la
page suivante.

Patentanmeldung Nr. Patent application No. Demande de brevet n°

99403161.5

Der Präsident des Europäischen Patentamts;
Im Auftrag

For the President of the European Patent Office

Le Président de l'Office européen des brevets
p.o.

I.L.C. HATTEN-HECKMAN

DEN HAAG, DEN
THE HAGUE, 29/11/00
LA HAYE, LE

THIS PAGE BLANK (USPTO)



Europäisches
Patentamt

European
Patent Office

Office européen
des brevets

Blatt 2 der Bescheinigung
Sheet 2 of the certificate
Page 2 de l'attestation

Anmeldung Nr.:
Application no.: 99403161.5
Demande n°:

Anmeldetag:
Date of filing: 16/12/99
Date de dépôt:

Anmelder:
Applicant(s):
Demandeur(s):
dmc2 Degussa Metals Catalysts Cerdec AG
60287 Frankfurt am Main
GERMANY

Bezeichnung der Erfindung:
Title of the invention:
Titre de l'invention:

Enamel composition for dielectric layers, white pigments with improved wettability contained therein and plasma display panel containing the dielectric layer

In Anspruch genommene Priorität(en) / Priority(ies) claimed / Priorité(s) revendiquée(s)

Staat:
State:
Pays:

Tag:
Date:
Date:

Aktenzeichen:
File no.
Numéro de dépôt:

Internationale Patentklassifikation:
International Patent classification:
Classification internationale des brevets:

C03C8/14, C03C17/04, C09C1/36, C09C3/04

Am Anmeldetag benannte Vertragsstaaten:
Contracting states designated at date of filing: AT/BE/CH/CY/DE/DK/ES/FI/FR/GB/GR/IE/IT/LI/LU/MC/NL/PT/SE/TR
Etats contractants désignés lors du dépôt:

Bemerkungen:
Remarks:
Remarques:

The applicant was transferred from:
CERDEC FRANCE S.A., 87000 LIMOGES/FR to
dmc2 DEGUSSA METALS CATALYSTS CERDEC AG
60287 frankfurt AM MAIN/DE on the 25.09.2000

THIS PAGE BLANK (USPTO)

Enamel composition for dielectric layers, white pigments
with improved wettability contained therein and plasma
display panel containing the dielectric layer

5 BACKGROUND OF THE INVENTION

The present invention relates to an enamel composition for
producing a reflecting white dielectric layer in plasma
display panels. The invention further relates to white
pigments with improved wettability which pigments are
10 present in the enamel composition. The invention still
further relates to a process for enamelling a glass
substrate for producing a reflecting dielectric layer with
improved properties in plasma display panels and plasma
display panels containing said reflecting dielectric layer.

15 A plasma display panel generally comprises two opposed
glass substrates, electrodes systematically arranged in the
glass substrates and a noble gas there between. More
particularly a plasma display panel (PDP) comprises a first
array of electrodes embedded in a dielectric layer on the
20 rear glass substrate, a second array of electrodes embedded
in a dielectric layer on a front substrate and a pattern of
a barrier for defining discharge spaces in between.

The structure and a process for producing a plasma display
panel (PDP) is described in the US 5,909,083. This document
25 also discloses the composition of transparent and pigmented
enamels such as used for a primer layer to be disposed on
glass substrate, a dielectric layer which covers the
address electrode and several compositions for producing
the barrier system. The dielectric layer forming
30 constituents essentially comprise a glass frit, based on
e.g. Bi_2O_3 , SiO_2 , ZnO and B_2O_3 , and a pigment like titanium
dioxide and in addition thereto aluminium oxide. The
mixture of said inorganic ingredients has a softening

temperature of 570 °C, and the fired enamel has a coefficient thermal expansion $\alpha = 80 \cdot 10^{-7} \text{ K}^{-1}$. For screen printing purposes the said enamel composition further contains a medium comprising a resin binder and an organic solvent system.

The US 5,948,537 relates to a non-crystallizable low melting glass compositions based on 52 to 68 wt.-% of $\text{PbO} + \text{Bi}_2\text{O}_3$, 14 to 28 wt.-% of B_2O_3 and 6 to 23 wt.-% of ZnO and facultatively small amounts of SiO_2 , Al_2O_3 , CeO_2 and SnO_2 . Said glass composition has a softening point of at most 510 °C and a thermal expansion coefficient α_{20}^{300} of 70 to 85 $\cdot 10^{-7} \text{ K}^{-1}$. This document is silent about the use of pigments within the dielectric layer. Other glass compositions for dielectric glass layers in PDP's consist of (wt.-%) 55 to 70 PbO , 6 to 25 B_2O_3 , 6 to 25 SiO_2 , 1 to 10 ZnO , 1 to 5 K_2O , Cr_2O_3 , CuO , NiO , MnO , CoO or vanadium oxide - see JP 10208644 A. A glass frit on the basis of a lead borosilicate containing (wt.-%): 62,4 to 69,6 PbO , 5,8 to 13,6 SiO_2 , 13,6 to 20 B_2O_3 , 0,2 to 1 Al_2O_3 , 0 to 5 MgO and 0 to 6 CaO for dielectric layers for PDP's is taught by JP-A 50-23414.

A glass frit composition for a dielectric layer in PDP's must fit several kind of specifications: Physical specifications like high compatibility with glass panels, an essentially complete ($\geq 99 \%$) coating at a firing temperature of preferably 550 bis 580 °C; optical specification like a reflection coefficient as great as possible to improve the luminance; electrical specification like a break down voltage greater than 400 V/25 μm . The glass frit compositions of the above cited documents do not fully meet the required properties in the one or other aspect. This happens especially in those cases where the glass composition contains a white pigment for providing the dielectric layer with a high reflection coefficient. One important problem the skilled has to cope with in using

enamel compositions containing white pigments for producing dielectric layers for PDP's is the porosity of said layers obtained by firing. The high porosity is most probably caused by the bad wetting properties of the pigments by the glass matrix. The quality of the reflecting dielectric layer for PDP's can be checked by light microscope observation and by sweep electron microscope observation - insufficient quality is characterized by an uneven surface aspect, a high number of bubbles and inhomogeneity of the micro structure.

It is a first object of the present invention to provide an enamel composition for producing a reflecting white dielectric layer for plasma display panels with improved properties, like especially a very low number of bubbles within the fired dielectric layer. Further objects of the invention are directed to provide a method for improving the wettability of white pigments for using them in an enamel composition for use in PDP's and a process for the production of glass layers with a porosity which is significantly lower than obtained by using conventional pigments. Further object of the invention can be seen from the following disclosure.

DISCLOSURE OF THE INVENTION

It has been found that the above stated object can be solved by using white pigments having an improved wettability whereby said improvement is achieved by a method comprising a heat treatment of a white pigment in the absence or presence of a low melting glass frit at 600 to 1000 °C. It has been found that heat treatment leads to a changement of the morphology of the pigment whereby the wettability is improved. By said heat treatment the specific area of a pigment is reduced and the mean partical size is increase. The thermally treated pigment is called „deactivated pigment“ whereby this term includes uncoated pigments as well as pigments which may be at least

partially coated with a low melting glass composition. In the latter embodiment the deactivation takes place by the coating with or without changing the morphology.

Therefore, the first object of the invention is solved by
5 an enamel composition for producing reflecting dielectric layers in plasma display panels, comprising as layer forming constituents 70 to 97 % by wt. of a glass frit composition having a softening temperature of less than 600 °C and 3 to 30 % by wt. of a particulate whitening
10 material, which is characterized in that the whitening material consists of at least 50 % by wt. of one or more thermally deactivated white pigments, 0 to 50 % by wt. of other white pigments and 0 to 20 % by wt. of one or more opacifiers and whereby the one or more thermally
15 deactivated white pigments have been made by a process comprising heating of at least white pigment in the absence or presence of a glass frit having a softening temperature of less than 600 °C at a temperature of 600 to 1000 °C for 0,1 to 10 hours. The sub-claims are directed to preferred
20 embodiments of the inventive enamel composition.

The enamel composition contains 70 to 97 % by wt., preferably 75 to 90 % by wt. and most preferred 80 to 90 % by wt. of a low melting glass frit composition. The glass frit composition may be comprised of one or more glass
25 frits, and the specified quantity includes also the glass frit by which according to one embodiment of the invention the thermally deactivated white pigment can be coated. The term „coated“ includes partially and essentially fully coated pigment particles. Usually coated pigments contain
30 up to 50 % by wt., preferably 20 to 40 % by wt. of a glass frit having a softening temperature of a less than 600 °C.

It is an important feature of the inventive enamel composition that the combination of all glass frits contained therein has a softening temperature of less than
35 600 °C, preferably less than 560 °C and most preferred a

softening temperature in the range of 390 to 520 °C. The said softening temperature T_s refers to a measurement using a Chevenard-dilatometer. At said temperature T_s , the glass frit becomes fluid and melts. According to a preferred
5 embodiment the glass frit composition of a coated pigment is equal or similar to the main part of the glass frit in the enamel composition.

In order to fully meet the electrical specification of the reflecting dielectric layer it is necessary, that a glass
10 layer made by firing said glass frit composition has a break-down voltage greater than 400 V/25 μm , preferably at least 1000 V/25 μm and most preferred equal or greater than 1500 V/25 μm .

Although there are known several types of low melting glass
15 frits for the respective application it has been found that a glass frit based on a lead borosilicate with a very low content of alkali metal oxide and/or earth alkali metal oxides are most preferred. A typical composition for such a glass frit which forms the matrix of the dielectric layer
20 consists essentially of (% by wt.): 55 to 90 PbO , 6 to 35 B_2O_3 , 6 to 40 SiO_2 , 0,1 to 2 CaO and/or BaO and 0,1 to 2 Na_2O and/or K_2O . Such compositions have a softening temperature in the range of 390 to 520 °C and a thermal expansion coefficient α_0^{300} of (60 to 90) $\cdot 10^{-7} \text{ K}^{-1}$. Such
25 preferred glass composition can be used not only for the inventive pigmented dielectric layers for plasma display panels but also for producing transparent glass layers which are used for embedding an array of electrodes on the back side of the front glass plate of a plasma display
30 panel. It is an essential advantage of the said glass frit composition that the glass layer made therefrom has a very high break-down voltage, which usually is around 2000 V/25 μm .

The enamel composition contains 3 to 30 % by wt. and
35 preferably 10 to 25 % by wt. of a particulate whitening

material. Although said whitening material may comprise a limited quantity of standard inorganic white pigments it is most preferred that the inventive enamel composition contains all white pigments in the form of thermally
5 deactivated pigments. Examples for white pigments are titanium dioxide in the form of rutile and anatase, tin oxide, zirconium silicate and barium sulfate. The most preferred white pigments are commercially available titanium dioxide pigments whereby the rutile gives a
10 slightly yellow tint and the anatase a slightly blue tint.

It has been found that by thermally deactivating such pigments the wettability of the pigments with respect to a glass matrix is substantially improved. As already said, it is suspected that the pigment surface is deactivated by
15 thermally treating of the pigment in the presence of or absence of a glass frit. It has also been found, that the specific area of a white pigment decreases and the mean particle size increases during the thermal treatment of the pigment at a temperature in the range of 600 bis 1000 °C or
20 even above the upper and below the lower limit of temperature. The heat treatment should not be performed at a too high temperature during a too long time in order to avoid a stoichiometric change of the pigment and thereby reduce the whiteness. Usually the heat treatment should be
25 performed in the temperature range of 600 to 1000 °C, preferably 600 to 800 °C.

The heat treatment of the white pigment for deactivating can, as disclosed above, be performed by simply heating the pigment at the temperature of 600 bis 1000 °C for 0,1 to 10
30 hours, preferably 0,3 to 3 hours. According to a preferred embodiment of this treatment process the white pigment is first transferred into briquettes; after the heat treatment of said briquettes they are crushed, e.g. by any milling process or the like, to fine particles. The fineness of
35 such deactivated white pigments usually corresponds to an

average particle size in the range of 0,5 to 5 μm , preferably 1 to 3 μm .

According to an alternative embodiment of the invention the thermal deactivation of the white pigment is performed by heating a mixture of a low melting glass frit and the white pigment. The heating temperature and the heating time correspond essentially to the conditions used for the diactivation of the pigment alone. According to a preferred method for deactivating a white pigment the method comprises the steps: (i) preparing a homogeneous powder mixture of a white pigment to be coated and a glass frit having a softening temperature of less than 600 °C, (ii) transferring the mixture into briquettes, (iii) heating said briquettes at a temperature of 600 to 1000 °C, preferably 600 to 800 °C for 0,1 to 10 hours, preferably 0,3 to 3 hours and (iv) crushing the so treated briquettes. A preferred powder mixture consists of at least 50 % by wt. of a white pigment and up to 50 % by wt. of a glass frit; an especially preferred mixture consists of 60 to 80 % by wt. of the pigment and 20 to 40 % by wt. of the glass frit. The term „briquette“ includes any kind of mouldings obtained by any pressing or granulating process. The mixing step (step i) is best performed by milling the pigment and the glass frit together whereby the milling process can be performed in the presence or absence of an organic solvent. The optimum temperature for the heating process and the heating time depend on the ratio glass/pigment and the fusibility of the glass matrix. The heat treatment can be made in any static or continuous oven. The obtained very compact lozènge can be first crushed and afterwards milled with the main part of the glass frit of the enamel composition (the other part of the glass frit corresponds to the coat of the deactivated pigment).

The reflection properties of the inventive enamel composition can in some cases further be improved by the

addition of an opacifying agent, such as an MgO , Al_2O_3 , some kinds of silicates, like micas, and ceramic glazes. Although such components can improve the reflective properties the presence is limited to 20 % of the whitening material and more preferably 5 % of the whitening material because said compounds are often very refractory and therefore may damage the surface aspect.

The inventive enamel composition may contain in addition to the layer forming constituents a liquid or thermoplastic printing medium. Preferred liquid enamel compositions comprise 60 to 80 % by wt. of layer forming constituents and 40 to 20 % by wt. of a liquid printing medium. The essential constituents of a printing medium are a polymer binder and at least a solvent system. The solvent system can be aqueous or organic, and the skilled in the art is familiar with the election of such compounds. It is necessary that the solvents are evaporatable and the polymer fully decomposable during the firing process. A typical aqueous printing medium essentially consists of hydroxypropyl cellulose, dipropylene glycol and water. A typical organic medium consists essentially of ethyl cellulose and pine oil. Of course, any printing medium as disclosed in any of the above cited documents can also be used.

As already described above in connection with the disclosure of the enamel composition the invention also includes a method for improving the wettability of white pigment for using them in an enamel composition for PDP's.

A further object of the invention is directed to a process for enamelling a glass substrate in order to get a reflecting dielectric layer on it. The process comprises usual steps which the skilled in the art is familiar with. Most usually an enamel composition consisting essentially of glass layer forming constituents dispersed in a liquid or thermoplastic medium is first printed on the substrate.

As far as necessary solvents are evaporated and the printing process is repeated several times in order to get the necessary thickness of the layer to be fired. The firing takes place at a temperature sufficiently below the strain temperature of the glass substrate and depending on the softening temperature of the enamel composition. Usually the firing temperature is in the range of 550 to 680 °C but, of course, a lower firing temperature is possible provided the enamel composition has a softening temperature significantly below 600 °C, like below 520 °C or preferably below 500 °C. This inventive process is characterized in that the inventive enamel composition is being used.

A further object of the invention is a plasma display panel comprising a first array of electrodes embedded in a dielectric layer on a rear substrate, a second array of electrodes embedded in a dielectric layer on a cover substrate (front plate) and a pattern of a barrier for defining discharge spaces in between of the rear and a front substrate; the inventive PDP is characterized in that the dielectric layer of the rear substrate is a reflecting, essentially white dielectric enamel made by coating the rear substrate with an enamel composition according to the invention and firing the coated substrate at a temperature in a range of 500 to 680 °C, preferably 540 to 580 °C. Details for producing PDP's can be taken out of the cited documents.

The inventive enamel composition and the dielectric layer made therefrom are characterized by the fact that they contain a deactivated white pigment. By deactivating the white pigment in the frame of the process of producing the enamel composition the wettability of the pigment could be significantly increased and thereby the properties of the fired dielectric layer could significantly be improved. The invention comprises several alternatives for deactivating

the white pigments. It is possible to select the best deactivating process and a specific enamel composition to achieve a well reflecting dielectric layer with optimum compatibility with the glass panel, high density of the layer, that means essentially free of enclosed bubbles, high reflection coefficient and good electrical properties like a high break-down voltage. It was not foreseeable that by a simply deactivating the white pigment it was possible to achieve the improvement of the properties of dielectric layers for use in plasma display panels.

EXAMPLES

Examples 1.1 to 1.9

Process for deactivating oxidic pigments in the absence of a glass frit. The oxide is agglomerated by pressing the pigment powder into briquettes of 2 cm square pressed under 100 N/cm². The briquettes are then heat-treated. Table 1 shows the tested pigments, the heat treatment conditions and some properties.

Table 1

No.	Pigment	T (°C)	t (hrs)	mean particle size d ₅₀ (μm)	specific area (m ² /g)	remarks
1.1	TiO ₂ (anatase)	-	-	0,5	19,6	white
1.2		800	1	1,3	12	white
1.3		1000	1	9,3	5,6	white
1.4		1200	1	22,1	1,7	slight yellow
1.5	TiO ₂ (rutile)	800	1	2,1	9,1	slight yellow
1.6	TiO ₂ (rutile)	1000	1	8,6	6,4	slight yellow
1.7	SnO ₂			1,5	10	white grey
1.8	CeO ₂			1,8	12	brown white
1.9	ZrSiO ₄			5,2	2,5	white grey

Examples 2.1 to 2.11

- 5 Process for deactivating oxidic pigments in the presence of a glass frit. Mixing a glass frit with the pigment in isopropanol in a ball mill. Drying in a static oven. Pressing the powder mixture into briquettes; heat-treatment of the briquettes; milling. Table 2 shows the conditions. Glass frit A has a softening temperature of 420 °C and
- 10 consists of (% by wt.): SiO₂ 5,8 %, B₂O₃ 14,8 %, PbO 73,2 %, Na₂O 0,1 %, K₂O 1,1 %. Glass frit B has a softening temperature of 440 °C and consists of (% by wt.): SiO₂ 6%, B₂O₃ 23 %, PbO 71 %. Glassfrit C has a softening

temperature of 470 °C and consists of (% by wt.) SiO₂ 6 %, B₂O₃ 34 % and PbO 60 %

Table 2

No.	Pigment	Glass frit	Pigment / Glass frit ratio	T (°C)	t (hrs)	deactivated pigment d ₅₀ (µm)	remarks
2.1	TiO ₂ (anatase)	A	20 : 80	450 (°C)	1 h	3,5	slightly linked
2.2	TiO ₂ (anatase)	A	20 : 80	540 (°C)	1 h	5,2	white; linked
2.3	TiO ₂ (anatase)	A	50 : 50	600 (°C)	1 h	4,1	white; linked
2.4	TiO ₂ (anatase)	A	50 : 50	800 (°C)	1 h	5,2	white; linked
2.5	TiO ₂ (anatase)	A	50 : 50	900 (°C)	1 h	6,5	white-grey; difficult to crush
2.6	TiO ₂ (anatase)	A	50 : 50	1000 (°C)	1 h	-	very difficult to crush
2.7	TiO ₂ (rutile)	A	30 : 70	450 (°C)	1 h	3,7	white
2.8	TiO ₂ (rutile)	A	40 : 60	600 (°C)	1 h	4,1	white; linked
2.9	TiO ₂ (rutile)	B	40 : 60	600 (°C)		3,9	white easy to mill
2.10	TiO ₂ (rutile)	C	40 : 60	600 (°C)	1 h	3,5	white
2.11	TiO ₂ (rutile)	C	40 : 60	800 (°C)	1 h	4,6	slightly yellow

Example 3. to 3.12

- General process for preparing the enamel composition. The glass frit (typ A composition SiO_2 5,8, B_2O_3 14,8, PbO 73,2, Na_2O 0,5 or type B composition SiO_2 6, B_2O_3 23, PbO 71) is
- 5 milled in isopropanol (20 g for 100 g of glass frit) up to a mean particle size in the range of 3 to 5 μm . The deactivated pigment, pure or coated with a glass coat and opacifiers are added during milling in order to get a homogeneous mixture. The whole is then dried.
- 10 The mixture of the glass layer forming constituents is then pasted in the usual manner by using a standard aqueous or organic medium for screen printing purposes in a quantity of approx 23-25 % by wt.:
- the aqueous medium is composed of hydroxyethyl cellulose
- 15 10 %, dipropylene glycol 30 % and water 60 %, the organic medium is composed of ethyl cellulose 3 % and pine oil 97 %.

Table 3 shows the compositions

Table 3

No.	glass frit Type/quantity (% by wt.)	deactivated pigment Type (product of example no.)/quantity (% by wt.)	opacifier Type/quant ity (% by wt.)	medium Type
3.1	A / 60 %	1.1 / 15 %	-	org. / 25
3.2	A / 67,5 %	1.2 / 7,5 %	-	org / 25
3.3	A / 60	1.2 / 15 %	-	org / 25
3.4	A / 56,25	1.2 / 18,75 %	-	org / 25
3.5	B / 63,75	1.2 / 11,25 %	-	org / 25
3.6	B / 63,75	1.6 / 11,25 %	-	org / 25
3.7	B / 52,50	2.3 / 22,50 %	-	org / 23
3.8	B / 52,50	2.8 / 22,50 %	-	org / 23
3.9	B / 52,50	2.9 / 22,50 %	-	org / 23
3.10	A / 60	1.2 / 15 %	Alumina 2	org / 23
3.11	A / 60	1.2 / 15 %	mica 2	org / 23
3.12	A / 60	1.2 / 15 %	-	aq / 25
3.13	B / 67.5	1.7 / 7.5	-	org / 25
3.14	B / 67.5	1.8 / 7.5	-	org / 25
3.15	B / 67.5	1.9 / 7.5	-	org / 25

Example 4.1 to 4.10

Method for producing a dielectric layer: Enamel

- 5 compositions according to examples of table 3) have been screen printed on a glass substrate. The thickness was around 25 μm . After drying the printing process has been repeated twice; the system has been fired.

Firing conditions and properties of the reflecting dielectric layer can be seen from table 4.

Table 4

No.	Enamel composition No.	T (°C)	t (hrs)	break-down voltage (V/25 μ m) 1)	reflection coefficient % at 440 nm ₂₎	Density 3)
4.1	3.1	580	1	850	60	--
4.2	3.2	580	1	820	40	++
4.3	3.3	580	1	810	55	+
4.4	3.4	580	1	830	60	+-
4.5	3.4	580	1,5	800	60	+
4.6	3.4	625	1	790	-	+
4.7	3.5	580	1	960	55	++
4.8	3.7	580	1	1020	50	++
4.9	3.8	580	1	990	50	++
4.10	3.9	580	1	1050	50	++
4.11	3.13	580	1	not determined	not determined	-- *)
4.12	3.14	580	1			-- *)
4.13	3.15	580	1			-- *)

- 5 1) The breakdown voltage is given by a dielectric rigidity test. The machine used here is from SEFELEC. A growing tension is applied to the system of capacitors and the detection of a defect (corresponding to the breakdown voltage) is made by the measurements of the electric current passing through a resistor.
- 10 An electronic memory allows to give the tension value at which the breakdown takes place. It is given in V/ μ m of thickness.

2) Determined by a Spectrocolorimeter ERIO JOHNE + REILHOFER,
working as a reflectometer for the measurement of the spectral
reflectance from 330 nm to 730 nm.

5 3) Presence of bubbles as observed by light microscope and by sweep
electron microscope

++ very dense = hardly any or very small bubbles

+ dense = small number of bubbles

- moderate = moderate quantity of bubbles

-- low density = high number of bubbles

10 *') Damage of the surface: not white

Claims:

1. Enamel composition for producing reflecting dielectric layers in plasma display panels, comprising as layer forming constituents 70 to 97% by weight of a glass frit composition having a softening temperature of less than 600°C and 3 to 30% by weight of a particulate whitening material, characterized in that the whitening material consists of at least 50 % by wt. of one or more thermally deactivated white pigments, 0 to 50 % by wt. of other white pigments and 0 to 20 % by wt. of one or more opacifiers and whereby the one or more thermally deactivated white pigments have been made by a process comprising heating of at least one white pigment in the absence or presence of a glass frit having a softening temperature of less than 600°C at a temperature of 600 to 1000°C for 0,1 to 10 hours.
2. Enamel composition according to claim 1, characterized in that the layer forming constituents comprise essentially 70 to 90 % by wt. of a glass frit composition having a softening temperature of less than 560 °C, 10 to 25 % by wt. of a deactivated white pigment which can be coated with a glass frit and 0 to 5 % by wt. of an opacifying agent.
3. Enamel according to claim 1 or 2, characterized in that the deactivated white pigment is made from titanium dioxide.
4. Enamel composition according to any of the claims 1 to 3, characterized in that the deactivated white pigment is made by a process, comprising transferring of a white pigment into briquettes, heating said briquettes at 600 to 1000 °C for 0,3 to 3 hours and crushing the so treated briquettes.

5. Enamel composition according to any of the claims 1 to 3, characterized in that the deactivation of the white pigment is made by a process comprising (i) preparing of a homogeneous powder mixture of at least 50 % by wt. of a glass frit having a softening temperature of less than 600 °C, (ii) transferring the mixture into briquettes, (iii) treating said briquettes at 600 to 800 °C for 0,3 to 3 hours and (iv) crushing the thermally treated briquettes.
6. Enamel composition according to any of the claims 1 to 5 characterized in that a glass layer made from said enamel composition by coating and firing has a breakdown voltage of greater than 400 V/25 µm.
7. Enamel composition according to any of the claims 1 to 6, characterized in that the glass frit composition is based on a lead borosilicate glass, essentially containing (wt.-%) PbO from 55 to 90 %, B₂O₃ from 6 to 35 %, SiO₂ from 6 to 40 %, CaO and BaO from 0,1 to 2 % and Na₂O and K₂O from 0,1 to 2 % and having a softening temperature T_s of 390 to 520 °C and a thermal expansion coefficient of (60 to 90) 10⁻⁷ K⁻¹.
8. Enamel composition according to any of the claims 1 to 7, characterized in that the layer forming constituents are dispersed in a liquid or thermoplastic medium.
9. Enamel composition according to claim 8, characterized in that it essentially consists of 60 to 80 % by wt. of layer forming constituents and 40 to 20 % by wt. of a liquid printing medium containing a polymer binder and at least a solvent system.
10. Method for improving the wettability of white pigments for using them in an enamel composition, characterized in that it comprises heating of a white pigment in the absence or presence of a glass frit having a softening

point of less than 600 °C at a temperature of 600 to 1000 °C for 0,1 to 10 hours.

11. Method according to claim 10, characterized in that it comprises the steps: (i) transferring of a white pigment into briquettes, (ii) heating said briquettes at a temperature of 600 to 1000 °C for 0,3 to 3 hours and (iii) crushing the so treated briquettes.
12. Method according to claim 10, characterized that it comprising the steps: (i) preparing a homogeneous powder mixture of at least 50 % by wt. of a white pigment and up to 50 % by wt. of a glass frit having a softening temperature of less than 600 °C, (ii) transferring the mixture into briquettes, (iii) heating said briquettes at a temperature of 600 to 800 °C for 0,3 to 3 hours and (iv) crushing the so treated briquettes.
13. Process for enamelling a glass substrate, comprising coating the substrate with an enamel composition consisting essentially of glass layer forming constituents dispersed in a liquid or thermoplastic medium and firing the coated substrate on a temperature in the range of 600 to 680 °C, characterized in that an enamel composition as to claim 8 is used.
14. Process according to claim 13, characterized in that the coating is performed by screen printing followed by drying.
15. Plasma display panels comprising a first array of electrodes embedded in a dielectric layer on a rear substrate, a second array of electrodes embedded in a dielectric layer on a cover substrate and a pattern of a barrier for defining discharge spaces in between, characterized in that the dielectric layer on the rear substrate is a reflecting essentially white enamel made

by coating the substrate with an enamel composition according to any of the claims 1 to 9 and firing at a temperature in the range of 600 to 680 °C.

ORIGINAL

Cabinet HERRBURGER

Summary

The invention refers to an enamel composition for producing reflecting dielectric layers in plasma display panels, comprising as layer forming constituents 70 to 97 % by wt. of a glass frit composition and 3 to 30 % by wt. of a particulate whitening material. The whitening material comprises one or more thermally deactivated white pigments, which have been made by a process comprising heating of at least one white pigment in the absence or presence of a glass frit having a softening temperature of less than 600 °C at a temperature of 600 to 1000 °C for 0,1 to 10 hours.

The invention further refers to a method for improving the wettability of white pigments by the above said thermal treatment.

15 The enamel is used for producing a reflecting white dielectric layer in plasma display panels.

ORIGINAL**Cabinet HERRBURGER**

